

BLANK PAGE



Indian Standard SPECIFICATION FOR FALLER BAR SLIDES FOR JUTE DRAWING FRAMES

UDC 677.052.983

© Copyright 1987

BUREAU OF INDIAN STANDARDS MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG NEW DELHI 110002

AMENDMENT NO. 1 OCTOBER 1997 TO

IS 11898: 1986 SPECIFICATION FOR FALLER BAR SLIDES FOR JUTE DRAWING FRAMES

(Page 4, clause 3.2.1) — Substitute 'IS 1586 : 1988*' for 'IS : 1586 - 1968*'.

(Page 4, clause 3.2.2) — Substitute 'IS 6416 : 1988†' for 'IS : 6416 - 1971†'.

(Page 4, clause 3.2.2) — Insert the following new clause after 3.2.2:

'3.3 Finish — The top surface of top and bottom slides shall be ground finish.'

(Page 4, foot-notes) — Substitute the following for the existing matter:

*Method for Rockwell hardness test for metallic material (Scales A-B-C-D-E-F-G-H-K) (second revision).

†Method of measuring case depth of steel (first revision).'

(Page 6, clause 6.1) — Insert the words 'and damage during transit' at the end of the sentence.

(TX 11)

Reprography Unit, BIS, New Delhi, India

Indian Standard

SPECIFICATION FOR FALLER BAR SLIDES FOR JUTE DRAWING FRAMES

Jute Mill Accessories and Jute Machinery Spare Parts Sectional Committee, TDC 17

Chairman

Representing

SHRIR. C. PANI

Members

SHRI P. K. BOSE (Alternate to

Shri R. C. Pani)

Dr Akash Chandra

SHRI P. G. GUPTA (Alternate)

SHRI A. K. BANERJEE SHRI R. P. CHATTERJEE (Alternate)

SHRI R. N. BANERJI

SHRI R. Y. CHURI (Alternate)

SHRI B. R. BASU

SHRI G. C. CHATTERJEE

SHRI G. D. DADOO SHRI S. K. DUTTA

SHRI G. MITRA (Alternate)

Seri H. N. Ghose

SHRI R. N. THAKAR (Alternate

SHRI D. GUPTA

SHRI M. GOSWAMI (Alternate)

SHRI D. S. JAIN

SHRIS. K. GHOSH (Alternate)

SHRI VINOD JAVERI

SHRI JAIN KOSHAL

SHRI K. M. MODI

THE Works MANAGER.

INDIAN PIN MEG Co (Alternate)

SHRI SITA RAM PODDAR

Dr S. R. RANGANATHAN

SHRI D. P. KHATUA (Alternate)

REPRESENTATIVE

SHRI S. M. TEWARI

SHRI R. I. MIDHA, Director (Tex) (Secretary)

The Lagan Jute Machinery Co Ltd, Calcutta

Forest Research Institute and Colleges, Dehra Dun

Britannia Engineering Co Ltd, Titagarh

Star Industrial & Textile Enterprises Ltd, Bombay

Office of the Jute Commissioner, Calcutta

Braithwaite & Co Limited, Calcutta

Birla Jute & Industries Ltd, Birlapur

Export Inspection Council of India, Calcutta

Indian Jute Mills Association, Calcutta

New Central Jute Mills Co Ltd, Calcutta

Shalimar Group Private Ltd, Howrah

Association of Merchants & Manufacturers of Textile

Stores & Machinery (India), Bombay

Textile Machinery Manufacturers' Association

(India), Bombay

Indian Pin Manufacturing Co, Calcutta

Hindusthan Bobbin Industries, Calcutta

Indian Jute Industries' Research Association,

Calcutta

Jute Manufactures Development Council, Calcutta

Thomas Duff & Co (India) Ltd, Calcutta

Director General, BIS (Ex-officio Member)

(Continued on page 2)

© Copyright 1987

BUREAU OF INDIAN STANDARDS

This publication is protected under the Indian Copyright Act (XIV of 1957) and reproduction in whole or in part by any means except with written permission of the publisher shall be deemed to be an infringement of copyright under the said Act.

IS: 11898 - 1986

(Continued from page 1)

Iute Mill Accessories and Jute Machinery Spare Parts Subcommittee, **TDC 17:2**

Convener

Representing

SHRI D. P. KHATUA

Indian Tute Industries' Research Association. Calcutta

Members

SHRI S. K. NEOGI (Alternate to Shri D. P. Khatua)

Dr Akash Chandra

SHRI P. G. GUPTA (Alternate)

SHRI A. K. BANERJEE

SHRI R. P. CHATTERJEE (Alternate)

SHRI A. N. BISWAS

SHRI I. CHAKRABARTI (Alternate)

SHRI P. K. CHAUDHURI

The India Machinery Co Ltd, Howrah

SHRI P. L. DASGUPTA (Alternate) SHRI D. K. DUTTA

SHRI K. K. DAS (Alternate)

SHRI S. K. DUTTA

SHRI G. MITRA (Alternate)

SHRI S. K. GHOSH

SHRI M. GOSWAMI

SHRI A. K. GUPTA (Alternate)

SHRI D. S. JAIN SHRI S. K. GHOSH (Alternate)

SHRI R. C. PANI

SHRI P. K. BOSE (Alternate) REPRESENTATIVE

SHRI R. K. SANGANARIA

SHRI P. K. CHATTERJEE (Alternate) SHRI R. N. THAKAR

Forest Research Institute and Colleges, Dehra Dun

Britannia Engineering Co Ltd, Titagarh

Guest, Keen, Williams Ltd. Howrah

Office of the Jute Commissioner, Calcutta

Export Inspection Council of India, Calcutta

Machinecare & Consultants, Calcutta New Central Jute Mills Co Ltd, Calcutta

Shalimar Group Private Ltd, Howrah

The Lagan Jute Machinery Co Ltd, Calcutta

Jute Manufactures Development Council, Calcutta Utex Industries, Calcutta

Indian Jute Mills Association, Calcutta

Indian Standard SPECIFICATION FOR FALLER BAR SLIDES FOR JUTE DRAWING FRAMES

O. FOREWORD

- 0.1 This Indian Standard was adopted by the Indian Standards Institution on 5 December 1986, after the draft finalized by the Jute Mill Accessories and Jute Machinery Spare Parts Sectional Committee had been approved by the Textile Division Council.
- 0.2 The need to publish this standard was felt in order to provide guidance to the manufacturers of faller bar slides for use in jute drawing frames. This would ensure the manufacturing of faller bar slides of acceptable quality and hence improving the efficiency and productivity of drawing frames in jute industry.
- 0.3 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS: 2-1960*. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

1. SCOPE

1.1 This standard prescribes requirements for faller bar slides for use in drawing frames in jute mill.

2. MATERIAL USED IN MANUFACTURE

2.1 Top and bottom slides shall be manufactured from steel conforming to designation 55C8 as per IS: 1570 (Part 2)-1979†.

^{*}Rules for rounding off numerical values (revised).
†Schedules for wrought steels: Part 2 Carbon steels (unalloyed steels) (first revision).

IS: 11898 - 1986

3. REQUIREMENTS

3.1 Dimensions — The dimensions of the faller bar slides shall be as agreed to between the manufacturer and the purchaser. The dimensions declared by the manufacturer shall be subject to the following tolerances:

Length, mm	士 0.25
Width, mm	+ 0·00 + 0·15
Thickness, mm	+ 0·00 - 0·15
Width of nose (for top slide only), mm	+ 0.00 - 0.12

- 3.2 The hardness of top slides shall be within 58 to 62 HRC with a case depth of 0.75 mm minimum. The bottom faller bar slides shall be hardened up to 25 mm from both the ends to a hardness of 55 to 65 HRC with a case depth of 0.75 mm minimum.
- 3.2.1 Hardness shall be determined by the method prescribed in IS: 1586-1968*.
- 3.2.2 Case depth shall be determined by the methods prescribed in IS: 6416-1971†.

4. MARKING

- 4.1 Each slide shall be legibly marked with the manufacturer's name or trade-mark.
- 4.1.1 The faller bar slides may also be marked with the Standard Mark.

Note — The use of the Standard Mark is governed by the provisions of the Bureau of Indian Standards Act 1986 and the Rules and Regulations made thereunder. The Standard Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well defined system of inspection, testing and quality control which is devised and supervised by BIS and operated by the producer. Standard marked products are also continuously checked by BIS for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the Standard Mark may be granted to manufacturers or producers may be obtained from the Bureau of Indian Standards.

5. SAMPLING AND CRITERIA FOR CONFORMITY

5.1 Lot — In any consignment, all the faller bar slides for jute drawing frames shall constitute a lot.

[•] Methods of Rockwell hardness test (B and C Scales) for steel (first revision). †Methods for measuring case depth of steel.

- 5.2 Samples shall be tested for each lot for ascertaining the conformity of the material to the requirements of this specification.
- 5.3 The number of faller bar slides for jute drawing frames to be chosen from the lot shall depend upon the size of the lot and shall be in accordance with Table 1.

TABLE 1 NUMBER OF FALLER BAR SLIDES FOR JUTE DRAWING FRAMES TO BE SELECTED

Lor Size	Sample Size	Acceptance Number	Sub-Sample Size	Acceptance Number for Sample
(1)	(2)	(3)	(4)	(5)
Up to 50	3	0	1	0
51 to 100	5	0	2	0
101 to 150	8	· 1	3	0
151 to 300	13	2	5	0
301 and abov	re 20	3	5	0

5.4 The faller bar slides for jute drawing frames shall be selected from the lot at random and in order to ensure the randomness of selection, the procedure given in IS: 4905-1968*, may be followed.

5.5 Number of Tests

- 5.5.1 Tests for dimensional requirements shall be conducted on the sample selected as given in col 2 of Table 1.
- 5.5.2 Tests for all other requirements given in this specification shall be conducted on sub-sample.

5.6 Criteria for Conformity

- 5.6.1 If any faller bar slide for jute drawing frame fails in any of the dimensional requirements given in this standard, it shall be declared as defective. The lot shall be declared as conforming to the requirements of dimensional characteristics if the number of defective faller bar slides for jute drawing frames is less than or equal to the corresponding acceptance number given in col 3 of Table 1.
- 5.6.2 For the other requirements tested on the sub-sample, any faller bar slide for jute drawing frame shall be declared as defective if it fails to meet any of the requirements other than dimensional requirements. The lot shall be declared as conforming to the requirements if the number of defective faller bar slides for jute drawing frames is less than

^{*}Methods for random sampling.

IS: 11898 - 1986

or equal to the corresponding acceptance number for sub-sample given in col 5 of Table 1.

5.6.3 The lot shall be declared as conforming to the requirements of this standard if 5.6.1 and 5.6.2 are satisfied.

6. PACKING

6.1 Faller bar slides shall be packed in such a way so as to ensure complete protection from rust.

BUREAU OF INDIAN STANDARDS

Headquarters:	
Manak Bhavan, 9 Bahadur Shah Zafar Marg, NEW DELHI 11	10002
Telephones: 331 0131 331 1375 Telegrams: Mai	
Regional Offices:	Telephone
*Western: Manakalaya, E9 MIDC, Marol Andheri (East) 6 BOMBAY 400093	32 92 95
†Eastern : 1/14 C. I. T. Scheme VII M, V. I. P. Road, Maniktola, CALCUTTA 700054	36 24 99
Northern: SCO 445-446, Sector 35-C CHANDIGARH 160036	{ 2 18 43 } 3 16 41
Southern : C. I. T. Campus, MADRAS 600113	41 24 42 41 25 19
	41 29 16
Branch Offices:	
'Pushpak', Nurmohamed Shaikh Marg, Khanpur AHMADABAD 380001	2 63 48 2 63 49
F' Block, Unity Bldg, Narasimharaja Square, BANGALORE 560002	22 48 05
Gangotri Complex, 5th Floor, Bhadbhada Road, T. T. Nagar, BHOPAL 462003	6 67 16
Plot No. 82/83, Lewis Road, BHUBANESHWAR 751002	5 36 27
53/5 Ward No. 29, R. G. Barua Road, 5th Byelane, GUWAHATI 781003	
5-8-56C L.N. Gupta Marg, HYDERABAD 500001	22 10 83
R14 Yudhister Marg, C Scheme, JAIPUR 302005	{ 6 34 71 6 98 32
117/418 B Sarvodaya Nagar, KANPUR 208005	{21 68 76 21 82 92
Patliputra Industrial Estate, PATNA 800013	6 23 05
Hantex Bldg (2nd Floor), Rly Station Road, TRIVANDRUM 695001	52 27
Inspection Office (With Sale Point):	
Institution of Engineers (India) Building, 1332 Shivaji Nagar, PUNE 411005	, 5 24 35
Sales Office in Bombay is at Novelty Chambers, Grant Road,	89 65 2 8
BOMBAY 400007 †Sales Office in Celcutta is at 5 Chowringhee Approach, P.O. Princep Street, CALCUTTA 700072	27 68 00